



## 1. Product Name

SprayLaq 680A Base Kote

## 2. Manufacturer

WOOD KOTE PRODUCTS INC  
8000 NE 14<sup>th</sup> PI (97211)  
PO Box 17192  
Portland OR 97217  
Tel: (800) 843-7666 (USA & Canada)  
Tel: (503) 285-8371  
Fax: (503) 285-8374  
[info@woodkote.com](mailto:info@woodkote.com)  
[www.woodkote.com](http://www.woodkote.com)

## 3. Product Description

### BASIC USE

SprayLaq 680A Base Kote is intended for professional use only. It is formulated as a first coat to seal interior wood surfaces and other interior surfaces that are compatible with lacquer in preparation for subsequent application(s) of opaque lacquer such as SprayLaq 680A white lacquer. SprayLaq 680A Base Kote may be applied to bare wood and is compatible with other Wood Kote products. Please refer to the *Wood Kote Schedule of Product Compatibility and Recommended Dry Times*. SprayLaq 680A Base Kote complies with the US Environmental Protection Agency (EPA) Volatile Organic Compound (VOC) emission requirements for Architectural and Industrial Maintenance coatings (effective 13Sep99).

### ADVANTAGES

- Easy to tint
- Fast-drying
- Economical
- High build
- Easy to sand

### COVERAGE

One application of SprayLaq 680A Base Kote will cover approximately 250-300sq ft/gal (6,1-7,4m<sup>2</sup>/L).

### COMPOSITION & PROPERTIES

SprayLaq 680A Base Kote is a flat-pigmented nitrocellulose-based lacquer. It is intended for application without thinning. If thinning is desired, LaqThin T-99A (lacquer thinner) should be used or, if regulations require a VOC-exempt thinner, use AceThin (acetone).

### TYPES

SprayLaq 680A Base Kote is available from the factory in one formulation. It can be tinted with Korreect-O or Perfect-O colorants to achieve a wide variety of custom colors.

### SIZES

SprayLaq 680A Base Kote is sold in 32-fl oz (946ml), 1-Gal (3,8L), 5-Gal (19L) and 55-Gal (208,5L) metal containers.

## 4. Technical Data

### PHYSICAL PROPERTIES

See table 1

## 5. Installation

Complete installation specifications and recommendations are available from the manufacturer.

### PREPARATORY WORK

#### Applicator Qualifications

All work shall be performed by skilled tradesmen experienced in performing work of this type and under the direction of a capable foreman.

#### Samples

For each finish system indicated at least two 8-1/2"x11" (19x24,6 cm) pieces should be provided for approval. If it is apparent conditions may allow substantial variations, a sufficient number of samples should be created to indicate the parameters of the variations. Those samples marked "approved" by architect/specifier shall serve as the standard for similar work throughout the project.



### Inspection

Verify all surfaces to be finished will be maintained within a temperature range of 45-80°F (7-27°C) during application and curing period. Verify all surfaces to be finished are clean and dry. Use an electric moisture meter to test all wood surfaces. Do not proceed if reading is higher than 15% without written permission from architect/specifier.

### Surface Preparation

Sand all wood surfaces in the direction of the wood grain with the appropriate abrasive grit specified on the finish schedules (usually between 80-220 grit). Sand all wood surfaces until all machine marks and glue are removed and each species has achieved a uniform smoothness without rough or burnished areas. Remove all sanding dust from the surfaces to be finished and from the work area.

### Mixing

Product should be thoroughly mixed prior to application. Please refer to *Wood Kote Lacquer & Polyurethane Stirring and/or Mixing Instructions*.

## APPLICATION

SprayLaq 680A Base Kote is formulated to be applied in-shop or on-site with a High Volume Low Pressure (HVLP) sprayer. Each coat should be applied at 0.003" (0,07





mm) wet film thickness in a manner that each application is uniform in sheen and color, must be free from sags, runs, bubbles or other defects detrimental to appearance or performance. The product is formulated to be applied when the ambient humidity is 30-70%. LaqAdd can be added to retard evaporation if application problems are caused by high temperature and/or humidity. Allow at least 30 minutes between applications. After the surface has adequately dried, it may be lightly sanded with 220-400 grit abrasive paper prior to the application of subsequent top-coats.

**PRECAUTIONS**

For on-site application, be certain local applicable VOC regulations do not supercede Federal regulations. Be certain that on-site conditions allow for adequate ventilation and pose no threat of fire or other health hazards. DO NOT apply over urethanes or other coatings that dry by oxidation. SprayLaq 680A Base Kote will combine with subsequent lacquer coatings. If subsequent coats are other than white, it is recommended to tint SprayLaq 680A Base Kote to approximate the color of the subsequent opaque lacquer. This product has been tested on a very limited number of substrates (and coatings). In addition, a very limited number of coatings have been tested over this product. The applicator is responsible for testing suitability and performance for the specific application. In all cases, Wood Kote strongly recommends

testing the entire finish system on an equivalent substrate before applying to the project. SprayLaq 680A Base Kote should only be applied by qualified professionals who have read and understood this information. Before using any chemical, read its label and Material Safety Data Sheet (MSDS).

**CLEAN UP**

Clean tools and surfaces with an absorbent cloth and LaqThin T-99A.

**6. Availability & Cost**

**AVAILABILITY**

SprayLaq 680A Base Kote is available through recognized Wood Kote retailers or directly from the manufacturer. A list of stocking dealers is available from the manufacturer and can be found on the manufacturer’s web site.

**COST**

Cost information is available from recognized Wood Kote retailers or from the manufacturer.

**7. Warranty**

SprayLaq 680A Base Kote is sold without warranty except that Wood Kote guarantees that the product is manufactured within the specifications provided herein. Unless Wood Kote warranties, in writing, specific products on an identified project, Wood Kote’s liability is limited to the replacement cost of the product. The information provided herein is accurate to the best of Wood Kote’s knowledge or

obtained by Wood Kote from sources believed by Wood Kote to be accurate. Wood Kote Products Inc does not assume any legal responsibility for use or reliance upon this information.

**8. Maintenance**

**STORAGE**

Keep in the original containers tightly closed when not in use and stored away from direct light at temperatures between 32-110°F (0-43°C).

**CLEANING & REPAIR**

SprayLaq 680A Base Kote is formulated as a first coat, and therefore, cannot be directly cleaned or repaired. If repair or replacement is desired, the entire finish system must be removed and reapplied. SprayLaq 680A Base Kote should be removed from wood with a chemical stripper (paint and varnish remover) or by mechanical means (sanding).

**DISPOSAL**

Dispose of only in accordance with local, state and federal regulations.

**9. Technical Services**

Additional information is available directly from the manufacturer and from the manufacturer’s web site.

**10. Filing Systems**

- Wood Kote–Product Catalog
- Additional product information is available from the manufacturer.
- [www.woodkote.com](http://www.woodkote.com)

Physical Properties Table 1

Mfr No	COLOR	GLOSS @ 60°	% WT SOLIDS	VOC gm/L	FLASH PT
4217A	White	N/A	47.4	<680	1°F (-17,2°C)